



ACCURATE FELT & GASKET

Material Specification

N-8051

Standard/Nonasbestos Gasket Material
F339000M9, Z1

Description

N-8051 is a light-duty material for low internal pressure and low flange pressure applications up to 13.8 MPa (2000 psi). It has a nitrile butadiene rubber binder for resistance to oil and is intended for applications with short duration maximum temperatures up to 180°C (350°F).

Obsoleted July 2022.

Specification Properties

Property	Value	Method
Compressibility, % (at 6.9MPa)	10 - 25	ASTM F 36
Recovery, %	40 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	2.76 (400) (min.)	ASTM F 152
Fluid Resistance, IRM901 Oil		ASTM F 146
Change in Volume, %	35 (max.)	
Fluid Resistance, Fuel A		ASTM F 146
Change in Volume, %	45 (max.)	
Binder Type	Nitrile Butadiene	

Remarks and Related Documents

Z1: Specification values determined by the conditioning and test methods required for ASTM F-104, Type 3 materials.

CONTACT

ADDRESS

3239 S. 51ST Ave.
Cicero, IL 60804

PHONE

708-780-9000

EMAIL

sales@afgco.com

WEBSITE

www.afgco.com

ISO CERTIFIED

9001:2015

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Accurate Felt & Gasket Mfg. Co. shall not be liable for any damages arising out of the use of any of its guide specifications.