ACCURATE FELT & GASKET

Material Specification

TS-9013

Thermo-Tork®/Nonasbestos Gasket Material
F729900E09M9

Description

TS-9013 is a controlled-swell material with latent cure styrene butadiene rubber binder and a blend of Aramid and cellulose fibers. It conforms well to irregular flange surfaces and is intended for water and oil applications with short duration maximum temperatures up to 290ºC (550ºF).

Specification Properties

Property	Value	Method
Density, g/cc(lb/cu.ft)	1.36 (85) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	12 - 25	ASTM F 36
Recovery, %	25 (min.)	ASTM F 36
Tensile Strength, AMD, MPa(psi)	8.28 (1200) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	30 - 70	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	20 - 50	
Binder Type	Styrene Butadiene	

Remarks and Related Documents

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

CONTACT

ADDRESS
3239 S. 51ST Ave.
Cicero, IL 60804

PHONE
708-780-9000

EMAIL
sales@afgco.com

WEBSITE
www.afgco.com

ISO CERTIFIED
9001:2015

Interface Performance Materials®, EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Syntheseal®, ThermoTork®, and Voltoid® are registered trademarks of Lydall Performance Materials (US), Inc.

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Accurate Felt & Gasket Mfg. Co. shall not be liable for any damages arising out of the use of any of its guide specifications.