

# ACCURATE FELT & GASKET MFG. COMPANY

3239 S. 51<sup>st</sup> Avenue

Cicero, IL 60804

Phone: 708-780-9000 Fax: 708-780-9009

www.afgco.com afg@afgco.com

## MATERIAL SPECIFICATION

### HFL-971

Hydro-Fused®/Nonasbestos Gasket Material

F729900E39M9

#### Description:

HFL-971 is a high density material with a combination of fully cured nitrile butadiene binder and thermoset resin for superior mechanical strength in heavy-duty applications. It has exceptional tensile strength, crush resistance, blowout resistance, erosion resistance, and resistance to shear and friction damage in dynamic joints. It is intended for applications sealing transmission fluid, axle lube, oil, fuel, coolant, water, and steam with short duration maximum temperatures up to 350°C (650°F).

#### Specification Properties:

Property	Value	Method
Density, g/cc(lb/cu.ft)	1.5 (93.6) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	7 - 17	ASTM F 36
Recovery, %	40 (min.)	ASTM F 36
Flexibility, Mandrel Bend, 12 X Ga.	No Cracks	ASTM F 147
Tensile Strength, AMD, MPa(psi)		ASTM F 152
Less Than 0.5mm Gauge	12.40 (1800) (min.)	
0.5 to 0.8mm Gauge	24.10 (3500) (min.)	
All Other Gauges	27.50 (3985) (min.)	
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	20 (max.)	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	20 (max.)	
Change in Weight, %	20 (max.)	
Binder Type	Fully Cured Nitrile Butadiene	

#### Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials, except where noted.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Synthesel®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

Revised 07/01/15

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Accurate Felt & Gasket Mfg. Co. shall not be liable for any damages arising out of the use of any of its guide specifications.

**ISO 9001: 2008 Registered**