



NC-711 CORK & RUBBER

BINDER: Nitrile Rubber
 CORK GRANULE SIZE: 0.5mm – 2mm

Physical Properties:

Test Method	Property	Specification
ASTM D2240	Hardness, Shore A	70-85
ASTM F36	Compressibility (400 psi), (%)	15-30
ASTM F36	Recovery, (%)	60% min.

Properties After Aging:

Test Method	Property	Specification
ASTM F146	Volume Change, ASTM #1, 70 hrs. at 100°C (%)	-10 to +10
	Volume Change, IRM 903, 70 hrs. at 100°C (%)	-5 to +15
	Volume Change, Fuel A, 22 hrs. at RT (%)	-5 to +10

CONTACT

ADDRESS
 3239 S. 51ST Ave.
 Cicero, IL 60804

PHONE
 708-780-9000

EMAIL
sales@afgco.com

WEBSITE
www.afgco.com

ISO CERTIFIED
 9001:2015

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Accurate Felt & Gasket Mfg. Co. shall not be liable for any damages arising out of the use of any of its guide specifications. 01/07/05