

# ACCURATE FELT & GASKET MFG. COMPANY

3239 S. 51<sup>st</sup> Avenue  
Cicero, IL 60804  
Phone: 708-780-9000 Fax: 708-780-9009  
www.afgco.com afg@afgco.com

## MATERIAL SPECIFICATION

### TS-9006

Thermo-Tork®/Nonasbestos Gasket Material  
F729900E09M5

#### Description:

TS-9006 is a heavy-duty, high density gasket material with fully cured styrene butadiene rubber binder. It is recommended for use in oil, water, and steam applications with high flange pressures and short duration maximum temperatures up to 350°C (650°F).

#### Specification Properties:

Property	Value	Method
Density, g/cc (lb/cu.ft)	1.52 (95) (min.)	ASTM F 1315
Compressibility, % (at 34.5MPa)	5 - 20	ASTM F 36
Recovery, %	40 (min.)	ASTM F 36
Tensile Strength, AMD, MPa (psi)	10.34 (1500) (min.)	ASTM F 152
Fluid Resistance, IRM903 Oil		ASTM F 146
Change in Thickness, %	20 - 60	
Fluid Resistance, Fuel B		ASTM F 146
Change in Thickness, %	15 - 40	
Binder Type	Fully Cured Styrene Butadiene	

#### Remarks and Related Documents:

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

Revised 07/01/15

The information on this data sheet is based on laboratory test data we believe to be accurate, relevant and reliable. Please look upon these values as guides rather than absolutes. Since actual service conditions for a given application may vary substantially from standard laboratory conditions, specific recommendations or warranties relative to a specific end use cannot be made. The buyer is urged to conduct its own investigations and qualification tests to determine suitability for its intended application. Accurate Felt & Gasket Mfg. Co. shall not be liable for any damages arising out of the use of any of its guide specifications.

ISO 9001: 2008 Registered